


e-Lite 70

OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	66 %	61 %
Visible Light Reflected (Int)	15 %	18 %
Visible Light Reflected (Ext)	16 %	21 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	23 %	25 %
Total Solar Energy Transmitted	36 %	33 %
Total Solar Energy Absorbed	41 %	42 %
Emissivity (Room Side)	0.73	0.73
Glare Reduction	27 %	25 %
Shading Coefficient	0.55	0.64
Solar Heat Gain Coeff. (G-Value)	0.48	0.56
U-Value Winter (IP)	0.98	0.46
U-Value Winter (SI)	5.59	2.64
Luminous Efficacy	1.20	0.95
Total Solar Energy Rejected	52 %	44 %

R081ISW e-Lite 70 Water Activated Adhesive
 R081IS7 e-Lite 70 Pressure Sensitive Adhesive



E4-BDS No 1911 January 2013